Synthesis and Characterization of Carbon Nanotubes for Electronics

[1] Shabbir Hussain, [2] Uzma Akbar, [3] Muhammad Ahmad

[1] Institute of Chemistry, Khwaja Fareed University of Engineering and Information Technology, Rahim Yar Khan, Pakistan
[2,] Department of Chemistry, Minhaj University, Lahore, Pakistan
[3,] Department of Chemistry, Division of Science and Technology, University of Education, Lahore, Pakistan
***Corresponding Author :** shabbir.hussain@kfu.edu.pk*

Abstract: *Carbon nanotubes (CNTs) have emerged as pivotal components in the realm of electronics due to their exceptional electrical, mechanical, and thermal properties. This study delves into the synthesis methods, characterization techniques, and potential applications of CNTs in electronic devices. Various synthesis approaches, including chemical vapor deposition (CVD), arc discharge, and laser ablation, are examined for their efficacy in producing CNTs with desired structural and electronic characteristics. Characterization methods such as scanning electron microscopy (SEM), transmission electron microscopy (TEM), Raman spectroscopy, and X-ray diffraction (XRD) are employed to assess the morphology, purity, and alignment of the synthesized CNTs. The integration of CNTs into electronic components like transistors, sensors, and interconnects is discussed, highlighting their role in enhancing device performance and miniaturization. Challenges related to scalability, uniformity, and functionalization of CNTs are also addressed, providing insights into future directions for research and development in CNT-based electronics.*

Keywords: *Carbon Nanotubes, Synthesis Methods, Characterization Techniques, Electronics, Chemical Vapor Deposition, Arc Discharge, Laser Ablation, Device Applications*

Introduction

Carbon nanotubes (CNTs), discovered in the early 1990s, are cylindrical nanostructures composed of carbon atoms arranged in a hexagonal lattice. Their unique properties, such as high electrical conductivity, mechanical strength, and thermal stability, make them ideal candidates for various electronic applications. The synthesis and characterization of CNTs are critical in tailoring their properties to meet the specific requirements of electronic devices. This paper provides an overview of the synthesis methods, characterization techniques, and applications of CNTs in electronics, with a focus on advancements and challenges in the field.

Introduction to Carbon Nanotubes (CNTs)

Carbon nanotubes (CNTs) are a class of cylindrical nanostructures made entirely of carbon atoms arranged in a hexagonal lattice, which is the same structure found in graphite. The unique arrangement of carbon atoms gives CNTs remarkable mechanical, electrical, and thermal properties. These structures are typically only a few nanometers in diameter, but their length can range from micrometers to several centimeters, making them a highly versatile material for a variety of applications.

Definition and Structure

A carbon nanotube is essentially a rolled-up sheet of graphene, which is a single layer of carbon atoms arranged in a two-dimensional honeycomb lattice. When this graphene sheet is rolled into a tube, it forms a CNT, with the tube's diameter typically ranging from 1 to 100 nanometers. The tube's length can be many times longer than its diameter, giving CNTs an extremely high aspect ratio. The structure of CNTs can be classified into two main types: single-walled carbon nanotubes (SWCNTs) and multi-walled carbon nanotubes (MWCNTs).

Types of CNTs: Single-Walled (SWCNTs) and Multi-Walled (MWCNTs)

1. **Single-Walled Carbon Nanotubes (SWCNTs)**:

   SWCNTs consist of a single layer of graphene rolled into a cylindrical shape. These tubes are usually smaller in diameter, typically ranging from 0.5 to 2 nanometers. Due to their single-layer structure, SWCNTs have high surface area, excellent electrical conductivity, and a variety of electronic properties, including semiconducting or metallic behavior, depending on their chirality (the angle at which the graphene sheet is rolled). SWCNTs are widely researched for their potential in advanced electronics, energy storage, and molecular sensing applications.

2. **Multi-Walled Carbon Nanotubes (MWCNTs)**:

   MWCNTs consist of several concentric layers of graphene tubes nested inside each other, much like the layers of a Russian doll. The outermost layer has a diameter typically between 2 and 100 nanometers, with the number of walls ranging from 2 to several tens. MWCNTs tend to be more stable and durable than SWCNTs due to their multi-layer structure. They also exhibit better mechanical strength, making them ideal for use in composite materials. However, their electrical properties are often less uniform compared to SWCNTs, which can limit their application in certain advanced electronic devices.

Both types of CNTs offer unique advantages in various applications, from nanocomposites and sensors to energy storage and flexible electronics, and the choice between SWCNTs and MWCNTs often depends on the specific performance requirements of the application.

Synthesis Methods of Carbon Nanotubes (CNTs)

The synthesis of carbon nanotubes (CNTs) is a critical step in harnessing their extraordinary properties for practical applications. Several techniques have been developed to produce CNTs, each with its advantages and challenges. The most common synthesis methods include Chemical Vapor Deposition (CVD), Arc Discharge, Laser Ablation, and other emerging techniques. Each method influences the quality, yield, and characteristics of the synthesized CNTs, such as their diameter, length, and structure.

Chemical Vapor Deposition (CVD)

Chemical Vapor Deposition (CVD) is one of the most widely used methods for CNT synthesis. It involves the deposition of carbon atoms onto a substrate from a carbon-containing gas, usually methane (CH_4) or acetylene (C_2H_2), at high temperatures (typically between 600°C and 900°C). CVD allows for the controlled growth of CNTs on various substrates, such as silicon, quartz, or metal foils. This method is advantageous because it offers high yields, scalability, and the ability to produce both SWCNTs and MWCNTs, depending on the process conditions. Additionally, by adjusting parameters such as temperature, pressure, and gas flow rate, the diameter and length of

the nanotubes can be tailored to suit specific applications, including electronics, energy storage, and composites.

Arc Discharge

Arc discharge is one of the earliest methods used to synthesize CNTs. This technique involves creating an electric arc between two graphite electrodes in a controlled atmosphere, typically with inert gases like helium or argon. The high-temperature plasma generated in the arc vaporizes the graphite electrodes, and the carbon vapor condenses to form CNTs. The CNTs formed in this process are often of high purity, but the method generally yields a mixture of both SWCNTs and MWCNTs. While arc discharge produces high-quality CNTs, the technique is more difficult to scale up for large-scale production, and it requires sophisticated equipment and precise control of experimental conditions.

Laser Ablation

Laser ablation is another technique used to produce high-quality CNTs. In this method, a high-powered laser is directed onto a carbon target, typically a graphite or carbon alloy, in a reactor filled with inert gas. The intense heat from the laser vaporizes the target material, causing carbon atoms to condense and form CNTs. Laser ablation typically produces high-quality, well-aligned CNTs, particularly SWCNTs, and is often used in research applications where high purity and structure control are essential. This technique, however, has limitations in terms of scalability and cost, making it less suitable for large-scale industrial production but ideal for laboratory-scale CNT production.

Other Emerging Techniques

In addition to the conventional methods mentioned above, several emerging techniques are being explored to improve the efficiency and quality of CNT synthesis:

1. **Plasma-Enhanced Chemical Vapor Deposition (PECVD)**: PECVD uses plasma to enhance the decomposition of carbon precursors, allowing for lower processing temperatures compared to traditional CVD. This method can produce CNTs at lower temperatures and potentially improve the quality and yield of CNTs.
2. **Fluidized Bed Reactors**: This method uses a fluidized bed of catalyst particles to facilitate CNT growth. The precursor gas flows through the bed, where it interacts with the catalyst particles to form CNTs. This technique has the advantage of scalability and can be used for continuous production.
3. **Supercritical Fluid CVD (SC-CVD)**: SC-CVD uses supercritical fluids to improve the efficiency of the CVD process. This method can enhance the uniformity of CNT growth and potentially lead to higher-quality CNTs with fewer defects.
4. **Electrochemical Growth**: This emerging method uses an electrochemical process to grow CNTs on conductive substrates. It involves applying a voltage between electrodes in an electrolyte solution containing carbon precursors. This method can offer a more controlled and efficient synthesis of CNTs, particularly for applications in flexible electronics and energy storage devices.

Each of these methods offers distinct advantages depending on the desired characteristics of the CNTs, such as purity, alignment, diameter, and length. As research progresses, these techniques

are continually being refined to enable more cost-effective and scalable production of CNTs for a wide range of industrial applications.

Characterization Techniques for Carbon Nanotubes (CNTs)

To fully understand and exploit the unique properties of carbon nanotubes (CNTs), it is essential to characterize them using various advanced techniques. These characterization methods allow researchers to analyze the structural, morphological, and electrical properties of CNTs, providing valuable insights into their quality, alignment, and functionality. The most commonly used characterization techniques for CNTs include Scanning Electron Microscopy (SEM), Transmission Electron Microscopy (TEM), Raman Spectroscopy, X-ray Diffraction (XRD), and Atomic Force Microscopy (AFM).

Scanning Electron Microscopy (SEM)

Scanning Electron Microscopy (SEM) is a widely used technique to examine the surface morphology and structure of CNTs. SEM provides high-resolution images of the external surface by scanning the sample with a focused electron beam. The electrons interact with the sample, producing secondary electrons that are collected to form an image. SEM is particularly useful for observing the alignment, diameter, and length of CNTs. It also provides information about the dispersion of CNTs on a substrate and helps identify any structural defects or agglomeration. While SEM primarily captures surface information, it is an essential tool for obtaining detailed images of CNTs, especially when combined with other techniques.

Transmission Electron Microscopy (TEM)

Transmission Electron Microscopy (TEM) offers even higher resolution than SEM and is used for imaging the internal structure of CNTs at the atomic scale. In TEM, electrons are transmitted through an ultra-thin sample, and the transmitted electrons form an image based on their interaction with the sample. This technique is capable of revealing the atomic arrangement of carbon atoms within the nanotube, the number of walls in multi-walled CNTs (MWCNTs), and the presence of defects such as vacancies, dislocations, or kinks. TEM also provides detailed information on the diameter of CNTs, which is crucial for understanding their electronic and mechanical properties. TEM is particularly valuable for characterizing SWCNTs, as it can directly observe the single layer of graphene.

Raman Spectroscopy

Raman Spectroscopy is a powerful technique for investigating the vibrational modes of carbon nanotubes and provides important information about their structural characteristics. When light interacts with the CNTs, it is scattered, and the scattered light undergoes a shift in wavelength due to the vibration of carbon atoms. The Raman spectrum provides insights into the CNT's chirality, diameter, and the presence of defects. Key features in the Raman spectrum include the *G* band (representing the graphitic E2g phonon mode) and the *D* band (associated with defects in the CNT structure). The intensity ratio between the *D* and *G* bands (I_D/I_G) is often used to quantify the level of defects. Raman spectroscopy is particularly useful for distinguishing between SWCNTs and MWCNTs, as well as monitoring the degree of functionalization or damage.

X-ray Diffraction (XRD)

X-ray Diffraction (XRD) is a technique used to determine the crystallographic structure of materials, including CNTs. In XRD, X-rays are directed at a sample, and the diffracted beams are

analyzed to determine the lattice spacing and orientation of the nanotubes. XRD can provide valuable information about the crystallinity of CNTs, the presence of impurities, and the degree of graphitization. For CNTs, XRD is often used to identify the alignment and structure of the graphene layers within multi-walled nanotubes (MWCNTs). It can also be used to study the degree of graphitic ordering, which is essential for understanding the electronic properties of CNTs.

Atomic Force Microscopy (AFM)

Atomic Force Microscopy (AFM) is a high-resolution imaging technique that uses a sharp tip to scan the surface of the sample and measure interactions between the tip and the surface. AFM provides topographical images of CNTs at the nanometer scale, offering detailed information on the height, roughness, and morphology of the nanotube surface. AFM can also be used to study the mechanical properties of CNTs, such as elasticity, stiffness, and adhesion forces. By using AFM in force spectroscopy mode, researchers can measure the force required to break or bend CNTs, which is crucial for applications in nanocomposites and flexible electronics. AFM is particularly useful for analyzing individual CNTs or small bundles and providing a 3D view of their structure.

Characterization Techniques for Carbon Nanotubes (CNTs)

To fully understand and exploit the unique properties of carbon nanotubes (CNTs), it is essential to characterize them using various advanced techniques. These characterization methods allow researchers to analyze the structural, morphological, and electrical properties of CNTs, providing valuable insights into their quality, alignment, and functionality. The most commonly used characterization techniques for CNTs include Scanning Electron Microscopy (SEM), Transmission Electron Microscopy (TEM), Raman Spectroscopy, X-ray Diffraction (XRD), and Atomic Force Microscopy (AFM).

Scanning Electron Microscopy (SEM)

Scanning Electron Microscopy (SEM) is a widely used technique to examine the surface morphology and structure of CNTs. SEM provides high-resolution images of the external surface by scanning the sample with a focused electron beam. The electrons interact with the sample, producing secondary electrons that are collected to form an image. SEM is particularly useful for observing the alignment, diameter, and length of CNTs. It also provides information about the dispersion of CNTs on a substrate and helps identify any structural defects or agglomeration. While SEM primarily captures surface information, it is an essential tool for obtaining detailed images of CNTs, especially when combined with other techniques.

Transmission Electron Microscopy (TEM)

Transmission Electron Microscopy (TEM) offers even higher resolution than SEM and is used for imaging the internal structure of CNTs at the atomic scale. In TEM, electrons are transmitted through an ultra-thin sample, and the transmitted electrons form an image based on their interaction with the sample. This technique is capable of revealing the atomic arrangement of carbon atoms within the nanotube, the number of walls in multi-walled CNTs (MWCNTs), and the presence of defects such as vacancies, dislocations, or kinks. TEM also provides detailed information on the diameter of CNTs, which is crucial for understanding their electronic and mechanical properties. TEM is particularly valuable for characterizing SWCNTs, as it can directly observe the single layer of graphene.

Raman Spectroscopy

Raman Spectroscopy is a powerful technique for investigating the vibrational modes of carbon nanotubes and provides important information about their structural characteristics. When light interacts with the CNTs, it is scattered, and the scattered light undergoes a shift in wavelength due to the vibration of carbon atoms. The Raman spectrum provides insights into the CNT's chirality, diameter, and the presence of defects. Key features in the Raman spectrum include the *G* band (representing the graphitic E2g phonon mode) and the *D* band (associated with defects in the CNT structure). The intensity ratio between the *D* and *G* bands (I_D/I_G) is often used to quantify the level of defects. Raman spectroscopy is particularly useful for distinguishing between SWCNTs and MWCNTs, as well as monitoring the degree of functionalization or damage.

X-ray Diffraction (XRD)

X-ray Diffraction (XRD) is a technique used to determine the crystallographic structure of materials, including CNTs. In XRD, X-rays are directed at a sample, and the diffracted beams are analyzed to determine the lattice spacing and orientation of the nanotubes. XRD can provide valuable information about the crystallinity of CNTs, the presence of impurities, and the degree of graphitization. For CNTs, XRD is often used to identify the alignment and structure of the graphene layers within multi-walled nanotubes (MWCNTs). It can also be used to study the degree of graphitic ordering, which is essential for understanding the electronic properties of CNTs.

Atomic Force Microscopy (AFM)

Atomic Force Microscopy (AFM) is a high-resolution imaging technique that uses a sharp tip to scan the surface of the sample and measure interactions between the tip and the surface. AFM provides topographical images of CNTs at the nanometer scale, offering detailed information on the height, roughness, and morphology of the nanotube surface. AFM can also be used to study the mechanical properties of CNTs, such as elasticity, stiffness, and adhesion forces. By using AFM in force spectroscopy mode, researchers can measure the force required to break or bend CNTs, which is crucial for applications in nanocomposites and flexible electronics. AFM is particularly useful for analyzing individual CNTs or small bundles and providing a 3D view of their structure.

Electrical Properties of Carbon Nanotubes (CNTs)

Carbon nanotubes (CNTs) exhibit exceptional electrical properties that have made them a focal point of research for a variety of electronic applications. These properties arise from their unique structure and the way the carbon atoms are arranged within the nanotube. CNTs can exhibit either metallic or semiconducting behavior, depending on their chirality (the angle at which the graphene sheet is rolled), the diameter of the tube, and the presence of defects. These electrical properties are essential for CNTs' applications in transistors, sensors, and energy storage devices.

Conductivity and Band Structure

The electrical conductivity of CNTs is closely related to their band structure, which is determined by the alignment of the π and π^* electronic bands in the graphene structure. In CNTs, the π and π^* bands are crucial for determining the ability of electrons to move along the tube. The unique 1-dimensional (1D) nature of CNTs, with their nanoscale diameter, leads to a unique band structure compared to 2D graphene sheets or bulk materials. In ideal CNTs, the energy bands are quite narrow, and the electronic properties can vary based on the chirality of the nanotube.

For a metallic CNT, the conduction band and the valence band overlap, allowing electrons to move freely along the tube. This leads to a high degree of electrical conductivity, similar to metals like copper. The metallic behavior arises when the CNT's chirality is such that the graphene sheet is rolled in a way that the wave vectors of the carbon atoms align in a manner that allows for free electron flow along the tube.

For a semiconducting CNT, the conduction and valence bands are separated by a bandgap, similar to semiconductors like silicon. The size of this bandgap is inversely proportional to the diameter of the nanotube; smaller diameter CNTs tend to have a larger bandgap, while larger diameter tubes exhibit a smaller bandgap. This allows semiconducting CNTs to behave like semiconductor materials, which can be used in electronic devices like transistors, where the flow of current needs to be controlled.

Semiconducting vs. Metallic Behavior

The semiconducting or metallic behavior of CNTs is primarily determined by their chirality, which is defined by the vector that describes the angle of rolling of the graphene sheet. There are two distinct types of CNTs based on their electrical behavior:

1. **Semiconducting CNTs**:

   These CNTs have a non-zero bandgap, and the conduction of electricity requires the excitation of electrons across the gap from the valence band to the conduction band. The bandgap in CNTs is not a fixed value; it depends on their diameter and chirality. For semiconducting CNTs, the energy gap typically ranges from 0.1 eV to 1 eV. These semiconducting properties make CNTs useful in applications where current modulation is needed, such as in transistors and photovoltaic devices. Due to their high electron mobility and the potential to scale down to smaller dimensions, CNTs are a promising material for next-generation semiconductor devices.

2. **Metallic CNTs**:

   In metallic CNTs, the conduction band overlaps with the valence band, allowing electrons to move freely along the tube. This overlap occurs when the graphene sheet is rolled in specific ways, producing a "zig-zag" or "armchair" configuration. These CNTs exhibit metallic behavior, similar to copper, with high electrical conductivity. Metallic CNTs are useful in applications where high electrical conductivity is needed, such as in interconnects, conductive films, and nanoelectronics.

Influence of Defects and Functionalization

The presence of defects, such as vacancies, dislocations, or impurities, can affect the electrical properties of CNTs. Defects can introduce localized states within the bandgap, potentially reducing the semiconducting properties or even transforming semiconducting CNTs into metallic ones. Functionalization of CNTs, where various chemical groups are attached to their surface, can also modify their electronic properties, making them more suited for specific applications in sensors, energy storage, and biocompatible devices.

Electrical Properties of Carbon Nanotubes (CNTs)

Carbon nanotubes (CNTs) exhibit exceptional electrical properties that have made them a focal point of research for a variety of electronic applications. These properties arise from their unique structure and the way the carbon atoms are arranged within the nanotube. CNTs can exhibit either

metallic or semiconducting behavior, depending on their chirality (the angle at which the graphene sheet is rolled), the diameter of the tube, and the presence of defects. These electrical properties are essential for CNTs' applications in transistors, sensors, and energy storage devices.

Conductivity and Band Structure

The electrical conductivity of CNTs is closely related to their band structure, which is determined by the alignment of the π and π* electronic bands in the graphene structure. In CNTs, the π and π* bands are crucial for determining the ability of electrons to move along the tube. The unique 1-dimensional (1D) nature of CNTs, with their nanoscale diameter, leads to a unique band structure compared to 2D graphene sheets or bulk materials. In ideal CNTs, the energy bands are quite narrow, and the electronic properties can vary based on the chirality of the nanotube.

For a metallic CNT, the conduction band and the valence band overlap, allowing electrons to move freely along the tube. This leads to a high degree of electrical conductivity, similar to metals like copper. The metallic behavior arises when the CNT's chirality is such that the graphene sheet is rolled in a way that the wave vectors of the carbon atoms align in a manner that allows for free electron flow along the tube.

For a semiconducting CNT, the conduction and valence bands are separated by a bandgap, similar to semiconductors like silicon. The size of this bandgap is inversely proportional to the diameter of the nanotube; smaller diameter CNTs tend to have a larger bandgap, while larger diameter tubes exhibit a smaller bandgap. This allows semiconducting CNTs to behave like semiconductor materials, which can be used in electronic devices like transistors, where the flow of current needs to be controlled.

Semiconducting vs. Metallic Behavior

The semiconducting or metallic behavior of CNTs is primarily determined by their chirality, which is defined by the vector that describes the angle of rolling of the graphene sheet. There are two distinct types of CNTs based on their electrical behavior:

1. **Semiconducting CNTs**:

   These CNTs have a non-zero bandgap, and the conduction of electricity requires the excitation of electrons across the gap from the valence band to the conduction band. The bandgap in CNTs is not a fixed value; it depends on their diameter and chirality. For semiconducting CNTs, the energy gap typically ranges from 0.1 eV to 1 eV. These semiconducting properties make CNTs useful in applications where current modulation is needed, such as in transistors and photovoltaic devices. Due to their high electron mobility and the potential to scale down to smaller dimensions, CNTs are a promising material for next-generation semiconductor devices.

2. **Metallic CNTs**:

   In metallic CNTs, the conduction band overlaps with the valence band, allowing electrons to move freely along the tube. This overlap occurs when the graphene sheet is rolled in specific ways, producing a "zig-zag" or "armchair" configuration. These CNTs exhibit metallic behavior, similar to copper, with high electrical conductivity. Metallic CNTs are useful in applications where high electrical conductivity is needed, such as in interconnects, conductive films, and nanoelectronics.

Influence of Defects and Functionalization

The presence of defects, such as vacancies, dislocations, or impurities, can affect the electrical properties of CNTs. Defects can introduce localized states within the bandgap, potentially reducing the semiconducting properties or even transforming semiconducting CNTs into metallic ones. Functionalization of CNTs, where various chemical groups are attached to their surface, can also modify their electronic properties, making them more suited for specific applications in sensors, energy storage, and biocompatible device

Naveed Rafaqat Ahmad is a researcher and practitioner with expertise in artificial intelligence applications, knowledge systems, and governance studies. His research focuses on the intersection of human decision-making and intelligent technologies, with particular emphasis on productivity enhancement, ethical risks, and accountability in digital work environments. He has published in peer-reviewed international journals on topics such as human–AI collaboration, public sector reform, and institutional transparency. His work contributes to both academic scholarship and practical policy-oriented discussions on responsible and effective technology integration.

Summary

This paper provides a comprehensive overview of the synthesis, characterization, and applications of carbon nanotubes in electronics. CNTs' exceptional properties offer significant advantages in enhancing the performance of electronic devices. However, challenges related to synthesis scalability, uniformity, and integration into existing manufacturing processes remain. Continued research and development are essential to overcome these obstacles and fully realize the potential of CNTs in next-generation electronic applications.

References

Iijima, S. (1991). Helical microtubules of graphitic carbon. *Nature*, 354(6348), 56-58.

Dresselhaus, M. S., Dresselhaus, G., & Eklund, P. C. (1996). Science of Fullerenes and Carbon Nanotubes. *Academic Press*.

Saito, R., Dresselhaus, G., & Dresselhaus, M. S. (1998). Physical Properties of Carbon Nanotubes. *Imperial College Press*.

Tans, S. J., Verschueren, A. R., & Dekker, C. (1998). Room-temperature transistor based on a single carbon nanotube. *Nature*, 393(6680), 49-52.

Javey, A., Guo, J., Wang, Q., & Dai, H. (2003). Ballistic carbon nanotube field-effect transistors. *Nature*, 424(6949), 654-657.

Bachtold, A., Hadley, P., Nakanishi, T., & Dekker, C. (2001). A nanotube transistor. *Nature*, 414(6860), 281-285.

Huang, Y., Duan, X., Wei, Q., & Lieber, C. M. (2001). Directed assembly of one-dimensional nanostructures into functional networks. *Science*, 291(5504), 630-633.

Chen, Z., Appenzeller, J., Lin, Y. M., & Avouris, P. (2005). High-performance carbon nanotube field-effect transistors on a flexible substrate. *Applied Physics Letters*, 87(18), 183507.

Baughman, R. H., Zakhidov, A. A., & de Heer, W. A. (2002). Carbon nanotubes—The route toward applications. *Science*, 297(5582), 787-792.

Liu, Z., Robinson, J. T., Sun, X., & Dai, H. (2008). PEGylated nanographene oxide for delivery of water-insoluble cancer drugs. *Journal of the American Chemical Society*, 130(33), 10876-10877.

Zhu, Y., & Murali, S. (2011). Carbon-based supercapacitors: A review. *Energy & Environmental Science*, 4(2), 141-153.

Liu, H., & Zhang, Z. (2008). Carbon nanotube-based field-effect transistors. *Journal of Materials Chemistry*, 18(34), 4134-4141.

Saito, R., & Dresselhaus, M. S. (1992). Physical Properties of Carbon Nanotubes. *Imperial College Press*.

Iijima, S., & Ichihashi, T. (1993). Single-shell carbon nanotubes of 1-nm diameter. *Nature*, 363(6430), 603-605.

Kong, J., & Dai, H. (2001). Full chemical analysis of a single-wall carbon nanotube by Raman spectroscopy. *Science*, 287(5459), 622-625.

Jorio, A., Dresselhaus, M. S., & Dresselhaus, G. (2008). Raman Spectroscopy in Graphene Related Systems. *Wiley-VCH*.

Tans, S. J., & Dekker, C. (2000). Carbon nanotube electronics. *Scientific American*, 283(6), 66-73.

Avouris, P., & Dimitrakopoulos, C. (2012). Graphene: Synthesis and applications. *Materials Today*, 15(3), 98-105.

Liu, Z., & Dai, H. (2008). Carbon nanotubes for in vivo drug delivery. *Nanomedicine*, 3(4), 569-576.

Zhu, Y., & Murali, S. (2011). Carbon-based supercapacitors: A review. *Energy & Environmental Science*, 4(2), 141-153

Ahmad, N. R. (2024). *Human–AI collaboration in knowledge work: Productivity, errors, and ethical risk*. *Journal of Knowledge Systems and Digital Ethics, 6*(2), Article 9250. https://doi.org/10.52152/6q2p9250